



Hawkhead, Inc
 1331 Pickettville Road
 Jacksonville, FL 32220
 Phone- 904-264-4295

PRODUCT DATA SHEET: HWK-3000 Fully Cured

PRODUCT DESCRIPTION: HWK-3000-F is a semi-rigid molded, fully cured medium coefficient material. The extruded material exhibits excellent fade and recovery stability with good rivet strength.

APPLICATION: HWK-3000-F is suitable for light to medium duty dry applications including bonded or riveted shoe brakes and bands.

PHYSICAL PROPERTIES: Width- Up to 13"
 Thickness- .125"-.500"
 Length- 15 foot rolls

FRICITION PROPERTIES:

Coefficient of Friction: Normal	.47
Hot	.47
@ 400 F.	.47
Static @ 200 F.	.52

Friction Code: GG

Recommended Operating Limits:

Max. Pressure, psi	250
Max. Rubbing Speed, ft/min.	4000
Temperature Max. F., intermittent	550
Temperature Max. F., continuous	500

COEFFICIENT OF FRICTION from SAE J661a test procedure

